

Mott Corporation

High Purity GasShield[®] Diffuser Products



mott *corporation*

84 Spring Lane, Farmington, CT 06032-3159
860-747-6333 Fax 860-747-6739
www.mottcorp.com

Mott Porous Metal Centering Ring Diffusers

GSD Series (GasShield® Diffuser)



Figure 1. Cross Section of the Centering Ring Diffuser

- 316LSS Porous Media in Various Grades
- Media Welded and Leak Tested
- Standard Vacuum Connection Sizes

Sizing Centering Ring Diffusers Selection Guide

- 1) Determine the size Centering Ring using Table 2.
- 2) Choose Media Grade using Table 4 to calculate acceptable flow to pressure drop. Use the Porous Area data in Table 2 to calculate the flux rate of lpm/in² by dividing the application flow rate in lpm by the porous area data in in².
- 3) To determine particle collection efficiency of the Media Grade, refer to Table 3. Note that diffusers are primarily used to reduce turbulence in the flow stream and not to reduce particulate. The porous material does however help to reduce particulate. If the need is for diffusion as well as a high level of filtration, see Filter Diffuser on Page 4.
- 4) Build the Catalog Number using Table 1. Note material composition of media, hardware and o-ring for compatibility with the process.

TABLE 1

MOTT CATALOG NUMBER CONFIGURATION

GSD	Connection Style	O-Ring Code	SS Media Grade Code	Standard Thickness
GasShield Diffuser Series-	CR (Centering Ring)-	16V (NW16 – 304SS/Viton)- 25V (NW25 – 316LSS/Viton)- 40V (NW40 – 316LSS/Viton)- 50V (NW50 – 316LSS/Viton)-	0.2 0.5 1 2 5 10 20	.039" (1.0mm) .047" (1.2mm) .047" (1.2mm) .062" (1.6mm) .062" (1.6mm) .062" (1.6mm) .062" (1.6mm)

Typical Part No.
GSD-CR-16V-0.2




Figure 2. Dimensions

TABLE 2

Centering Rings	O-Ring Materials	Body Materials	A OD Inch/mm	B Porous Dia. Inch/mm	Active Porous Area Inch ²
NW-16	Viton	304 SS	0.67 / 17.0	0.63 / 16.0	0.25
NW-25	Viton	316LSS	1.02 / 25.9	0.98 / 24.9	0.60
NW-40	Viton	316LSS	1.61 / 40.9	1.57 / 39.9	1.75
NW-50	Viton	316LSS	2.05 / 52.1	1.97 / 50.0	2.80

Mott Porous Metal Centering Ring Diffusers

GSD Series (GasShield® Diffuser)

Air Efficiency

TABLE 3

Media Grade	Particle Size, μm		
	Initial Collection Efficiency		
	90%	99%	99.9%
0.2	A	B	0.2
0.5	A	0.25	0.3
1	A	0.35	0.7
2	0.3	0.6	2
5	0.8	2	5
10	4.5	8	13
20	8	12	20


Testing performed per IBR E304

Tested at flux of 1.2 slpm/in^2

A = Initial efficiency is greater than 90% for all particle sizes

B = Initial efficiency is greater than 99% for all particle sizes

TABLE 4



- Differential pressure varies in direct proportion to sheet thickness. Standard sheet thickness varies with media grade.
- Flow curves are presented in a log-log format; be sure to note the correct numerical values for each log cycle.
- Flow characteristics given are for porous media only.
- These flow characteristics were derived using 316LSS porous media.
- These flow characteristics are typical and should be used for general reference only.

Mott Porous Metal Filter/Diffusers

GSE Series (GasShield® Filter/Diffusers)

9 log reduction (99.9999999%) in particles down to 0.003 µm at rated flow; confirmed at the Most Penetrating Particle Size of 0.08µm.

- 316LSS or Nickel Porous Media
- 316LSS Hardware Connection
- Variety of End Connections

Sizing Filter Diffusers

- 1) Determine the application flow rate in slpm.
- 2) Choose a Filter Diffuser from Table 6 that has a max flow rating equal to or greater than the application flow rate. Confirm the flow/delta P using Table 5 to confirm that pressure drop is acceptable for system pressures and flows.
- 3) Choose a connection type and build a Catalog Number from Table 6.
- 4) Table 7 defines dimensions per Figure 3. Note material composition of filter media and hardware for compatibility with the process.




Figure 3. Face Seal

TABLE 5 Nitrogen Flow vs Differential Pressure
Mott GSE Series Filter/Diffusers




TABLE 6

MOTT CATALOG NUMBER CONFIGURATION

GSE	Connection Style	Flow Rate/Media Material
GasShield Filter/Diffuser Series-	V1 (1/4" VCR)- T1 (1/4" Tube Stub)-	10S (10 slpm / 316LSS) 20N (20 slpm / Nickel) 40N (40 slpm / Nickel)
Typical Part Number: GSE -V1-10S		

TABLE 7 (Dimensions)

Flow Rate/ Media Material	Element OD Inch/mm	Element Length Inch/mm	A OAL Inch/mm	B Inch/mm
10 slpm/ 316LSS	0.50 / 12.7	1.50 / 38.1	2.39 / 60.7	0.75 / 19.1
20 slpm / Nickel	0.50 / 12.7	0.75 / 19.1	1.64 / 41.7	0.75 / 19.1
40 slpm / Nickel	0.50 / 12.7	1.50 / 38.1	2.39 / 60.7	0.75 / 19.1

mott corporation

84 Spring Lane, Farmington, CT 06032-3159
860-747-6333 Fax 860-747-6739
www.mottcorp.com



HPDIFFUSERS REV 0 0503